





# Bona Domo

Rivestimento monocomponente a base d'acqua

La soluzione facile per i pavimenti domestici.

## DATI TECNICI

<b>Tipo di prodotto:</b>	Miscela monocomponente di poliuretano acrilato a base d'acqua
<b>Contenuto di solidi:</b>	ca. 28%
<b>Lucentezza (a 60°):</b>	Silkmatt 40%, Matt 18% (su vetro)
<b>Diluizione:</b>	Se necessario, diluire con Bona Retarder al 4% per un tempo di apertura più lungo.
<b>Tempo di asciugatura:</b>	Seconda mano: 1-2 ore* Uso leggero: 8 ore* Copertura possibile: 7 giorni* *in condizioni climatiche normali, 20°C/60% R.H.
<b>Strumenti di applicazione:</b>	Rullo Bona o pennello.
<b>Dosaggio:</b>	8-10 m <sup>2</sup> /litro (100-120g/m <sup>2</sup> ) per mano
<b>Sicurezza:</b>	Unclassified
<b>Pulizia:</b>	Pulire gli attrezzi da residui di materiale con Bona Hands&Tools Cleaner.
<b>Durata:</b>	Un anno dalla data di produzione nel contenitore originale non aperto.
<b>Stoccaggio/trasporto:</b>	La temperatura non deve scendere al di sotto di +5°C o superare +30°C durante lo stoccaggio o il trasporto
<b>Smaltimento:</b>	I rifiuti e i contenitori vuoti devono essere gestiti in conformità con le normative locali.
<b>Confezioni:</b>	3 x 5 litri

Ulteriori informazioni sono riportate nell'apposita scheda di sicurezza

## PREPARAZIONE

Assicurarsi che il pavimento sia acclimatato alla sua destinazione d'uso. La superficie deve essere levigata fino al legno nudo, asciutta e priva di polvere di carteggiatura, olio, cera o altri contaminanti.

Lasciare che il prodotto raggiunga la temperatura ambiente. Le condizioni ottimali di applicazione sono comprese tra 18-25°C e 30-60% di umidità relativa dell'aria. Alte temperature e basse percentuali di umidità accorciano i tempi di asciugatura, basse temperature e alte percentuali di umidità le allungano.

**La temperatura minima di utilizzo è di 13°C.**





# Bona Domo

ONE COMPONENT, WATERBORNE COATING

The easy solution for domestic floors.

## IMPORTANT!

- Plasticisers found in materials such as carpet underlays, furniture legs, castors and adhesives used for fixing can lead to softening and discolouration. Exposure to hair dyes or rubber tyres on cars, cycles and baby strollers can lead to permanent, irreversible discolouration of the surface. Use protection or completely avoid contact.
- Spills should be removed promptly. Unattended spills may cause cosmetic stains or damage the surface. Please note that whilst Bona lacquers are designed to provide a sealed surface that is resistant to wear, scuffing and spillage, etc. No surface applied finish system can prevent physical damage to the timber or "harden" the floor. Indentations in the wood and scratches may be caused by furniture, dropped items, dog claws, etc. and steps should be taken to reduce the possibility of this occurring.

The information in this document and all other advice and recommendations that we provide to help and assist the applicator are based on previous experience and extensive testing but makes no claim to be complete. Because of the wide range of possible uses and conditions of application of our products, we do not relieve users from the need to carry out their own trials or to seek technical advice from Bona before use. Bona can only guarantee its products and not the construction as a whole. Observe recommendations from flooring manufacturer and the provisions of relevant standards.